





## COLOR CHART


*Siliconized Modified Polyester (SMP)*



COOL  
BRIGHT WHITE




COOL  
POLAR WHITE



COOL  
LIGHT STONE



COOL  
SAHARA TAN



COOL  
DESERT BEIGE




COOL  
EMERALD GREEN




COOL  
COUNTRY RED



COOL  
HAWAIIAN BLUE



COOL  
ASH GRAY



COOL  
CHARCOAL




COOL  
COPPER PENNY



COOL  
KOKO BROWN



COOL  
WEATHERED COPPER



COOL  
DARK BRONZE  
\*KYNAR



COOL  
ZINC METALLIC  
\*KYNAR



GALVALUME®

\*\*\*\*Depending on color and coil availability some colors may not be painted in a Becker Specialty ®BeckrySil system.

*These color samples are as close as possible to actual colors offered, within the limitations of color reproduction.*

# 40 YEAR LIMITED WARRANTY



## ®BECKRYSIL SUPER COOL

Beckers ®BeckrySil Super Cool is our warranted Silicone Modified Polyester (SMP). Beckers ®BeckrySil Super Cool coatings use solar reflective pigmentation to ensure outstanding durability, combined with a primer containing anti-corrosion pigments to ensure excellent resistance to corrosive elements. ®BeckrySil Super Cool coatings retain their color, resist chalking and fading and provide energy savings year after year.

®BeckrySil Super Cool is Energy Star Compliant. ®BeckrySil Super Cool offers superior color retention and superior chalk resistance when compared to other SMP's on the market. ®BeckrySil Super Cool provides excellent flexibility and hardness.

Western States Decking, Inc. (WSDI), offers a 40 year film adhesion warranty. ®BeckrySil Super Cool will not chip, crack, check, peel, (except for such crazing that may occur on tightly, roll-formed edges and brake bends on non-standard custom items). WSDI offers a 35 year chalk and fade warranty. Chalk in excess of a number 8 rating in accordance with ASTM D-659. Fade for color change in excess of 5 units in accordance with ASTM D-2244.

## PERFORMANCE CHARACTERISTICS

Specification	Test		Results
ASTM D-523	60° Specular Gloss	10-45	Gardner 60° meter or equivalent
ASTM D-3363	Pencil Hardness	H-3H	No Break in the film
ASTM D-4145	Coating Flexibility	1T-2T	No pick off with Scotch #610 tape Substrate specific
ASTM D-2794	Reverse Impact 60-80 inch pounds	Passes	No pick off with Scotch #610 tape
ASTM G-53	Q.U.V. Weatherometer 1000 hours	Passes	No objectionable chalking per ASTM D-659, color change per ASTM D-2244 Or blistering per ASTM D-714
ASTM D-2247	Humidity, 1000 hours At 100 F and 100% Humidity	Passes	Less than 5% No. 8 Blisters
ASTM B-117	Salt Spray 1000 hours 5% Salt Solution	Passes	Less than 5% No. 6 blisters and Less than 1/8" creep or tape off from the Scribe per ASTM D-1654
ASTM D-2244-89	45 So. Florida Exposure 20 years, color retention	Passes	No objectionable color change Less than 5 units color change
ASTM D-659-86	45 So. Florida Exposure 20 years, chalk resistance	Passes	No objectionable color change Rating of 6 min.

### Beckers Industrial Coatings - Americas

2526 Delta Lane  
Elk Grove Village, IL 60007  
USA

Tel. 847-766-3555  
Fax. 847-766-3595  
info-beckerspecialty@beckers-bic.com  
[www.beckers-bic.com](http://www.beckers-bic.com)

Subsidiary of AB Wilh. Becker  
Bruksgården  
SE-263 83  
Sweden